

ML SP. Z O.O.

82-300 Gronowo Górne
ul. Berylowa 7
POLAND
VAT No. 578 311 88 60
Phone: +48 55 235 09 85

TECHNICAL DATA SHEET

GRAYFIN PPH

Test:	Value:	Test method:
MFR (230°C/2,16 kg):	5-8 g/10 min	ISO 1133
Density ¹⁾ :	0,95 g/cm ³	ISO 1183
Young's Modulus:	< 1500 MPa	ISO 527
Ultimate tensile strength:	> 25 MPa	ISO 527
Charpy V-notched impact strength 23°C (±2°C):	< 4,5 kJ/m ²	ISO 179
Ash content:	< 7,0 %	ISO 3451-1
Material structure:	Granulate	ML Polyolefins
Type:	PP homo	ML Polyolefins
Colour:	Light gray / Dark gray	ML Polyolefins
Filtration:	160 µm	ML Polyolefins

¹⁾ Fluctuation: ±5%

The data and information in this document are approximate values, based on our current level of knowledge and experience, and they do not represent sales offer. This document does not give any assurance, liability and warranty of specified product. High quality ML compounds are entirely or partially produced from non-prime ingredients. Although the selection of the raw materials, the production and the quality control is being done according the common best practices and it is the buyer's responsibility to inspect and test ML products in order to determine the suitability for the buyer's application.